

G**T****P**

GT Products *Condensation System* Thixotropic Additive **GT 6125**

January 08

DESCRIPTION

GT 6125 is a one to three percent by weight additive that is specifically formulated for brush on molding.

After mixing into GT-5092, GT-6142, or GT-6143 the material will thicken to a creamy, butterable product that can easily be brushed on to vertical or overhead surfaces without sagging or running. A thin layer of non-thixotropic silicone material should be applied first to capture detail and achieve a bubble free surface. The rubber will cure in 24 hours at room temperature.

